



Low Energy & No CO₂ Emission Bricks

Fly Ash & Pond Ash Bricks



Property	As Cured	Heat Stabilized, 800 C
Density, g/cc	1.7 to 1.8	1.6 to 1.7
Compression Strength, Psi	3,500	> 3,500
pH	10 to 11	8.5 to 9.5
Water intake, 24 hr immersion	<13 %	TBD
Efflorescence	Mild	No

